

Life Expectancy

Total sheet life 40 years or more with correct maintenance

Expected time to first full repainting		Wall Cladding		Roof Cladding	Reduction due to orientation, Years	
Standard colours	Nearest BS ref ²	Inland	Marine ³		E, W	S, SE, SW
Bamboo	08C35	30 years	25 years	20 years	0	-4
Buttermilk	10C31					
Goosewing Grey	10A05					
Ivory	RAL9002					
Merlin Grey	18B25					
Moorland Green	12B21					
Mushroom	10B19					
New Grey	10B23					
Olive Green	12B27					
Pigeon Grey	18B17					
Wedgwood Blue	18C37					
White ¹	00E55					
Willow	12B17					
Black	00E53	25 years	20 years		-2	-5
Cornflower Blue*	18E53					
Country Green*						
Crimson	RAL3004					
Golden Glow	06E56					
Golden Yellow*	08E51					
Forest Green	RAL6002					
Jade	14C37					
Juniper Green*	12B29					
Linden Green*	12E53					
Navy	RAL5003					
New Red	04D44					
Ocean Blue	18C39					
Pacific Blue	18E58					
Poppy Red	04E53					
Saffron	08E53					
Sage Green*	12D45					
Slate Blue*	18B29					
Tangerine Orange	06E53					
Terracotta	04C39					
Vandyke Brown	08B29					

30 years
 25 years
 20 years

¹ Where colourmatching on white (00E55) is critical, it is important that the material is purchased from the same production batch.

² These numbers are for guidance only, as the colours vary slightly from British Standard.

³ Within 1 1/2 miles of shoreline

* Additional building colours available from DOBEL.

Substrate: DOBEL 200 EXTERIOR is available on Hot Dipped Zinc Galvanised Steel to BS EN 10142:1991.

Overpainting of the underside of lapped edges, together with the exposed cut edge, may be advisable for some severe industrial, coastal and marine environments; as in some conditions the substrate properties are included in the total sheet life. The standard reverse coating is specifically designed for bonding most injected insulation foams and laminating of slab.

Certain colours, in specific instances, may well have a longer period to first maintenance than shown in the above table. For advice please contact Dobel.

Dobel

– SSAB Swedish Steel Group –

SSAB Dobel Coated Steel Limited,
Narrowboat Way, Hurst Business Park,
Brierley Hill, West Midlands. DY5 1UF
Telephone: 01384 74660
Fax: 01384 77575

